



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09D 5/44, C08G 18/16	A1	(11) International Publication Number: WO 98/07795 (43) International Publication Date: 26 February 1998 (26.02.98)
(21) International Application Number: PCT/US97/13367 (22) International Filing Date: 29 July 1997 (29.07.97) (30) Priority Data: 08/700,978 21 August 1996 (21.08.96) US (71) Applicant: PPG INDUSTRIES, INC. [US/US]; One PPG Place, Pittsburgh, PA 15272 (US). (72) Inventors: ZAWACKY, Steven, R.; 124 Old English Road, Pittsburgh, PA 15237 (US). ZWACK, Robert, R.; 3049 Swansea Crescent West, Allison Park, PA 15101 (US). McCOLLUM, Gregory, J.; 5130 Bronwyn Court, Gibsonia, PA 15044 (US). ESWARAKRISHNAN, Venkatachalam; 1896 Caribou Drive, Allison Park, PA 15101 (US). COLERIDGE, Edward, R.; 695 Cornell Drive, Lower Burrell, PA 15068 (US). (74) Agents: STACHEL, Kenneth, J.; PPG Industries, Inc., One PPG Place, Pittsburgh, PA 15272 (US) et al.		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>With amended claims.</i>

(54) Title: ELECTRODEPOSITABLE COATING COMPOSITIONS AND METHOD FOR IMPROVED CURE RESPONSE**(57) Abstract**

An improved electrodeposable composition is provided comprising: (a) an active hydrogen-containing cationic resin electrodeposable on a cathode; (b) a capped polyisocyanate curing agent; and (c) an organotin-containing catalyst. The improvement comprises the addition to the electrodeposable composition of a water immiscible acid functional compound having a hydrocarbon chain of at least 5 carbon atoms like abietic acid and natural sources thereof. A preferred acid functional compound is abietic acid. The composition provides improved cure response and appearance properties when electrodeposited over conductive substrates.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KN	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

ELECTRODEPOSITABLE COATING COMPOSITIONS
AND METHOD FOR IMPROVED CURE RESPONSE

5
BACKGROUND OF THE INVENTION

This application is a continuation-in-part of copending U.S. Patent application Serial No. 08/329,106, filed on October 24, 1994.

10
FIELD OF THE INVENTION

The present invention relates to cationic electrodepositable compositions, and to their use in electrodeposition.

15
BACKGROUND OF THE INVENTION

The application of a coating by electrodeposition involves depositing a film-forming composition to an electrically conductive substrate under the influence of an applied electrical potential. Electrodeposition has gained prominence in the coatings industry because in comparison with non-electrophoretic coating methods, electrodeposition provides higher paint utilization, outstanding corrosion resistance, and low environmental contamination. Early attempts at commercial electrodeposition processes used anionic electrodeposition, where the workpiece being coated served as the anode. However, in 1972, cationic electrodeposition was introduced commercially. Since that time, cationic electrodeposition has become increasingly popular and today is the most prevalent method of electrodeposition. Throughout the world, more than 80 percent of all motor vehicles manufactured are given a primer coating by cationic electrodeposition.

Many cationic electrodeposition compositions used today are based on active hydrogen-containing resins derived from a polyepoxide and a capped polyisocyanate curing agent. These

35

- 2 -

cationic electrodeposition compositions contain organic tin catalysts such as dibutyl tin oxide to activate cure of the electrodeposition composition. Because of cost and environmental considerations, the levels of these tin catalysts are kept low. Organotin catalysts are relatively expensive and appear in the ultrafiltrate of electrodeposition baths, which can present waste disposal problems. However, low catalyst levels may lessen the cure response of a coating composition, providing weaker properties in the cured film than desired. Appearance of the cured film may also be adversely affected.

It would be desirable to provide an electrodepositable composition which demonstrates enhanced cure response at low organotin catalyst levels without loss of cured film properties including humidity resistance, adhesion, and appearance.

SUMMARY OF THE INVENTION

In accordance with the present invention, an improved electrodepositable composition and a method of electrodeposition using the composition are provided. The electrodepositable composition comprises (a) an active hydrogen-containing cationic resin electrodepositable on a cathode; (b) a capped polyisocyanate curing agent; and (c) an organotin-containing catalyst. The improvement comprises the addition to the electrodepositable composition of at least one water immiscible acid functional compound having a hydrocarbon chain of at least 5 carbon atoms. The water immiscible acid functional compound is preferably polycyclic.

DETAILED DESCRIPTION

The cationic resin of the present invention is preferably derived from a polyepoxide and can be prepared by reacting together a polyepoxide and a polyhydroxyl group-containing

- 3 -

material selected from alcoholic hydroxyl group-containing materials and phenolic hydroxyl group-containing materials to chain extend or build the molecular weight of the polyepoxide. The reaction product can then be reacted with a cationic salt group former to produce the cationic resin.

A chain extended polyepoxide is typically prepared as follows: the polyepoxide and polyhydroxyl group-containing material are reacted together neat or in the presence of an inert organic solvent such as a ketone, including methyl isobutyl ketone and methyl amyl ketone, aromatics such as toluene and xylene, and glycol ethers such as the dimethyl ether of diethylene glycol. The reaction is typically conducted at a temperature of about 80°C to 160°C for about 30 to 180 minutes until an epoxy group-containing resinous reaction product is obtained.

The equivalent ratio of reactants; i.e., epoxy:polyhydroxyl group-containing material is typically from about 1.00:0.50 to 1.00:2.00.

The polyepoxide preferably has at least two 1,2-epoxy groups. In general the epoxide equivalent weight of the polyepoxide will range from 100 to about 2000, typically from about 180 to 500. The epoxy compounds may be saturated or unsaturated, cyclic or acyclic, aliphatic, alicyclic, aromatic or heterocyclic. They may contain substituents such as halogen, hydroxyl, and ether groups.

Examples of polyepoxides are those having a 1,2-epoxy equivalency greater than one and preferably about two; that is, polyepoxides which have on average two epoxide groups per molecule. The preferred polyepoxides are polyglycidyl ethers of polyhydric alcohols such as cyclic polyols. Particularly preferred are polyglycidyl ethers of polyhydric phenols such as Bisphenol A. These polyepoxides can be produced by etherifi-

cation of polyhydric phenols with an epihalohydrin or dihalohydrin such as epichlorohydrin or dichlorohydrin in the presence of alkali. Besides polyhydric phenols, other cyclic polyols can be used in preparing the polyglycidyl ethers of cyclic polyols. Examples of other cyclic polyols include alicyclic polyols, particularly cycloaliphatic polyols such as 1,2-cyclohexane diol and 1,2-bis(hydroxymethyl)cyclohexane. The preferred polyepoxides have epoxide equivalent weights ranging from about 180 to 2000, preferably from about 186 to 1200.

10 Epoxy group-containing acrylic polymers can also be used. These polymers typically have an epoxy equivalent weight ranging from about 750 to 2000.

Examples of polyhydroxyl group-containing materials used to chain extend or increase the molecular weight of the polyepoxide (i.e., through hydroxyl-epoxy reaction) include alcoholic hydroxyl group-containing materials and phenolic hydroxyl group-containing materials. Examples of alcoholic hydroxyl group-containing materials are simple polyols such as neopentyl glycol; polyester polyols such as those described in U.S. Patent No. 4,148,772; polyether polyols such as those described in U.S. Patent No. 4,468,307; and urethane diols such as those described in U.S. Patent No. 4,931,157. Examples of phenolic hydroxyl group-containing materials are polyhydric phenols such as Bisphenol A, phloroglucinol, catechol, and resorcinol. Mixtures of alcoholic hydroxyl group-containing materials and phenolic hydroxyl group-containing materials may also be used. Bisphenol A is preferred.

The active hydrogens associated with the cationic resin include any active hydrogens which are reactive with isocyanates within the temperature range of about 93 to 204°C, preferably about 121 to 177°C. Typically, the active hydrogens are selected from the group consisting of aliphatic hydroxyl and

- 5 -

primary and secondary amino, including mixed groups such as hydroxyl and primary amino. Preferably, the cationic resin will have an active hydrogen content of about 1 to 4 milliequivalents, more preferably about 2 to 3 milliequivalents of active hydrogen per gram of resin solids.

The resin contains cationic salt groups, which are preferably incorporated into the resin molecule as follows: The resinous reaction product prepared as described above is further reacted with a cationic salt group former. By "cationic salt group former" is meant a material which is reactive with epoxy groups and which can be acidified before, during, or after reaction with the epoxy groups to form cationic salt groups. Examples of suitable materials include amines such as primary or secondary amines which can be acidified after reaction with the epoxy groups to form amine salt groups, or tertiary amines which can be acidified prior to reaction with the epoxy groups and which after reaction with the epoxy groups form quaternary ammonium salt groups. Examples of other cationic salt group formers are sulfides which can be mixed with acid prior to reaction with the epoxy groups and form ternary sulfonium salt groups upon subsequent reaction with the epoxy groups.

When amines are used as the cationic salt formers, monoamines are preferred, and hydroxyl-containing amines are particularly preferred. Polyamines may be used but are not recommended because of a tendency to gel the resin.

Tertiary and secondary amines are preferred to primary amines because primary amines are polyfunctional with respect to epoxy groups and have a greater tendency to gel the reaction mixture. If polyamines or primary amines are used, they should be used in a substantial stoichiometric excess to the epoxy functionality in the polyepoxide so as to prevent gelation and the excess amine should be removed from the reaction mixture by

vacuum stripping or other technique at the end of the reaction. The epoxy may be added to the amine to ensure excess amine.

Examples of hydroxyl-containing amines are alkanolamines, dialkanolamines, trialkanolamines, alkyl alkanolamines, and
5 aralkyl alkanolamines containing from 1 to 18 carbon atoms, preferably 1 to 6 carbon atoms in each of the alkanol, alkyl and aryl groups. Specific examples include ethanolamine, N-methylethanolamine, diethanolamine, N-phenylethanolamine, N,N-dimethylethanolamine, N-methyldiethanolamine, triethanolamine
10 and N-(2-hydroxyethyl)-piperazine.

Amines such as mono, di, and trialkylamines and mixed aryl-alkyl amines which do not contain hydroxyl groups or amines substituted with groups other than hydroxyl which do not negatively affect the reaction between the amine and the epoxy
15 may also be used. Specific examples include ethylamine, methylethylamine, triethylamine, N-benzyl dimethylamine, dicocoamine and N,N-dimethylcyclohexylamine.


Mixtures of the above mentioned amines may also be used.

The reaction of a primary and/or secondary amine with the
20 polyepoxide takes place upon mixing of the amine and polyepoxide. The amine may be added to the polyepoxide or vice versa. The reaction can be conducted neat or in the presence of a suitable solvent such as methyl isobutyl ketone, xylene, or 1-methoxy-2-propanol. The reaction is generally exothermic and
25 cooling may be desired. However, heating to a moderate temperature of about 50 to 150°C may be done to hasten the reaction.

The reaction product of the primary and/or secondary amine and the polyepoxide is made cationic and water dispersible by at
30 least partial neutralization with an acid. Suitable acids include organic and inorganic acids such as formic acid, acetic acid, lactic acid, phosphoric acid and sulfamic acid. By

- 7 -

"sulfamic acid" is meant sulfamic acid itself or derivatives thereof; i.e., an acid of the formula:



wherein R is hydrogen or an alkyl group having 1 to 4 carbon atoms. Sulfamic acid is preferred. Mixtures of the above mentioned acids may also be used.

The extent of neutralization varies with the particular reaction product involved. However, sufficient acid should be used to disperse the electrodepositable composition in water. Typically, the amount of acid used provides at least 20 percent of all of the total neutralization. Excess acid may also be used beyond the amount required for 100 percent total neutralization.

In the reaction of a tertiary amine with a polyepoxide, the tertiary amine can be prereacted with the neutralizing acid to form the amine salt and then the amine salt reacted with the polyepoxide to form a quaternary salt group-containing resin. The reaction is conducted by mixing the amine salt with the polyepoxide in water. Typically, the water is present in an amount ranging from about 1.75 to about 20 percent by weight based on total reaction mixture solids.

In forming the quaternary ammonium salt group-containing resin, the reaction temperature can be varied from the lowest temperature at which the reaction will proceed, generally room temperature or slightly thereabove, to a maximum temperature of about 100 °C (at atmospheric pressure). At higher pressures, higher reaction temperatures may be used. Preferably, the reaction temperature is in the range of about 60 to 100°C. Solvents such as a sterically hindered ester, ether, or

- 8 -

sterically hindered ketone may be used, but their use is not necessary.

In addition to the primary, secondary, and tertiary amines disclosed above, a portion of the amine that is reacted with the polyepoxide can be a ketimine of a polyamine, such as is described in U.S. Patent No. 4,104,147, column 6, line 23 to column 7, line 23. The ketimine groups decompose upon dispersing the amine-epoxy resin reaction product in water.

In addition to resins containing amine salts and quaternary ammonium salt groups, cationic resins containing ternary sulfonium groups may be used in the composition of the present invention. Examples of these resins and their method of preparation are described in U.S. Patent Nos. 3,793,278 to DeBona and 3,959,106 to Bosso et al.

The extent of cationic salt group formation should be such that when the resin is mixed with an aqueous medium and other ingredients, a stable dispersion of the electrodepositable composition will form. By "stable dispersion" is meant one that does not settle or is easily redispersible if some settling occurs. Moreover, the dispersion should be of sufficient cationic character that the dispersed resin particles will migrate toward and electrodeposit on a cathode when an electrical potential is set up between an anode and a cathode immersed in the aqueous dispersion.

Generally, the cationic resin in the electrodepositable composition of the present invention contains from about 0.1 to 3.0, preferably from about 0.1 to 0.7 milliequivalents of cationic salt group per gram of resin solids. The cationic resin is preferably non-gelled, having a number average molecular weight ranging from about 2000 to about 15,000, preferably from about 5000 to about 10,000. By "non-gelled" is meant that the resin is substantially free from crosslinking,

- 9 -

and prior to cationic salt group formation, the resin has a measurable intrinsic viscosity when dissolved in a suitable solvent. In contrast, a gelled resin, having an essentially infinite molecular weight, would have an intrinsic viscosity too high to measure.

The electrodepositable composition of the present invention also contains a capped polyisocyanate curing agent. The polyisocyanate curing agent may be a fully capped polyisocyanate with substantially no free isocyanate groups, or it may be partially capped and reacted with the resin backbone as described in U.S. Patent 3,984,299. The polyisocyanate can be an aliphatic or an aromatic polyisocyanate or a mixture of the two. Diisocyanates are preferred, although higher polyisocyanates can be used in place of or in combination with diisocyanates.

Examples of suitable aliphatic diisocyanates are straight chain aliphatic diisocyanates such as 1,4-tetramethylene diisocyanate and 1,6-hexamethylene diisocyanate. Also, cycloaliphatic diisocyanates can be employed. Examples include isophorone diisocyanate and 4,4'-methylene-bis-(cyclohexyl isocyanate). Examples of suitable aromatic diisocyanates are p-phenylene diisocyanate, diphenylmethane-4,4'-diisocyanate and 2,4- or 2,6-toluene diisocyanate. Examples of suitable higher polyisocyanates are triphenylmethane-4,4',4"-triisocyanate, 1,2,4-benzene triisocyanate and polymethylene polyphenyl isocyanate.

Isocyanate prepolymers, for example, reaction products of polyisocyanates with polyols such as neopentyl glycol and trimethylol propane or with polymeric polyols such as polycaprolactone diols and triols (NCO/OH equivalent ratio greater than one) can also be used. A mixture of

- 10 -

diphenylmethane-4,4'-diisocyanate and polymethylene polyphenyl isocyanate is preferred.

Any suitable aliphatic, cycloaliphatic, or aromatic alkyl monoalcohol may be used as a capping agent for the polyisocyanate in the composition of the present invention including, for example, lower aliphatic alcohols such as methanol, ethanol, and n-butanol; cycloaliphatic alcohols such as cyclohexanol; aromatic-alkyl alcohols such as phenyl carbinol and methylphenyl carbinol. Glycol ethers may also be used as capping agents. Suitable glycol ethers include ethylene glycol butyl ether, diethylene glycol butyl ether, ethylene glycol methyl ether and propylene glycol methyl ether. Diethylene glycol butyl ether is preferred among the glycol ethers.

Other suitable capping agents include oximes such as methyl ethyl ketoxime, acetone oxime and cyclohexanone oxime and lactams such as epsilon-caprolactam.

The polyisocyanate curing agent is usually present in the electrodepositable composition in an amount ranging from about 5 to 60 percent by weight, preferably from about 25 to 50 percent by weight based on total weight of resin solids.

Organotin catalysts are also present in the electrodepositable composition of the present invention, preferably in the form of a dispersion. The catalysts, which are often solids, are typically dispersed in a conventional pigment grinding vehicle such as those disclosed in U.S. Patent 4,007,154, by a grinding or milling process. The catalysts are typically used in amounts of about 0.05 to 1 percent by weight tin based on weight of resin solids. Suitable catalysts include dioctyltin oxide and dibutyltin oxide.

At low organic tin levels in conventional systems, the appearance of the cured coating can be a problem. The presence of the acid functional compound in the electrodepositable

- 11 -

composition allows for the use of relatively low levels of organic tin catalyst; i.e., from about 0.05 to 0.5 percent tin by weight based on weight of resin solids, with good cure response and appearance properties.

5 The acid functional compound added to the electrodepositable composition of the present invention is water immiscible so as to be electrodepositable on the cathode, and has a hydrocarbon chain (excluding carbon atoms associated with the acid functionality; i.e., with the carboxyl group) of at
10 least 5 carbon atoms, preferably from about 5 to about 34 carbon atoms, more preferably from about 9 to about 34 carbon atoms, and most preferably about 15 to 19 carbon atoms.

Preferred acid functional compounds are carboxylic acids. The acid functional compound can be monocarboxylic acid
15 functional or may contain more than one acid functional group. The hydrocarbon chain of the acid functional compound may be aliphatic or aromatic, may be saturated or unsaturated, and may be branched, linear, or cyclic, including polycyclic. The hydrocarbon chain of the acid functional compound may also be
20 substituted. Examples of substituents include hydroxyl groups. Examples of aliphatic saturated carboxylic acids include isodecanoic acid, lauric acid, hexanoic acid, dimer fatty acid, and stearic acid. Examples of aliphatic unsaturated carboxylic acids include oleic acid, 9-11 octadecadienoic acid, 9-12
25 octadecadienoic acid (linoleic acid), linolenic acid, and mixtures thereof. Examples of substituted carboxylic acids include 12-hydroxy stearic acid.

Suitable polycyclic carboxylic acids useful as the water immiscible acid functional compound with a hydrocarbon chain
30 length of at least 5 carbon atoms include abietic acid, which is preferred as well as natural sources of abietic acid. Natural sources of abietic acid of varying purity include gum rosin,

- 12 -

wood rosin, and tall oil rosin. Abietic acid may be used in its natural form or it may be purified using techniques known to those skilled in the art before being added to the electro-depositable composition of the present invention. For example, dihydroabietic acid and dehydroabietic acid can be used in mixtures with each other and with abietic acid. In its natural form as a rosin or rosin acid, the abietic acid may be present with isomeric forms such as levopimaric and resin acids of the pimaric type having a phenanthrene nucleus. The natural sources can also include the oleoresin material with the presence some or all of the turpentine oils or distillates. Since rosin is a complex mixture of mainly twenty carbon atom fused ring, monocarboxylic acids and a small amount of nonacidic components, where the resin acid molecule has the double bonds and the carboxylic acid group, any derivative can be used that maintains the carboxylic acid group. For example, hydrogenated derivatives of the oleoresin and rosin can be used. One suitable example of abietic acid containing tall oil that can be used is Unitol NCY partially hydrogenated tall oil from Union Camp, Savannah, Georgia.

The acid functional compound may be incorporated into the electrodepositable composition in several ways. It may be added to the final reaction mixture of the main vehicle; i.e., the active hydrogen-containing resin, just before solubilization with water and acid as described above. Alternatively, it may be added to a partially solubilized resin kept at sufficiently high solids so as to be sheared into the final composition. By "partially solubilized" is meant that the resin is fully neutralized with respect to acid functionality, but only partially water-thinned; i.e., diluted. Additionally, it may be co-dispersed with polyepoxide-polyoxyalkylene-polyamine modifying anti-crater resins such as those described in U.S.

- 13 -

Patent No. 4,423,166. It may also be dispersed in a conventional pigment grinding vehicle such as those disclosed in U.S. Patent 4,007,154, by a grinding or milling process, and be a component of a pigment paste.

5 The acid functional compound is added to and present in the electrodepositable composition in the form of an acid; i.e., it is not formed in situ by the decomposition or hydrolysis of a metal salt or catalyst. The acid functional compound is added to the electrodepositable composition as a compound containing free
10 acid functional groups. Moreover, the acid functional compound is not reacted into the cationic resin backbone; i.e., to form an epoxy ester during the epoxy extension reaction, nor does it serve to any substantial extent to solubilize the main vehicle. Though not intending to be bound by any particular theory, it is
15 believed that because of the immiscibility of the acid functional compounds, they do not protonize well and hence do not solubilize the main vehicle as do the specific acids such as sulfamic acid, lactic acid, etc., mentioned above that are added for the purpose of solubilization of the main vehicle.

20 The acid functional compound is usually present in the electrodepositable composition in an amount ranging from about 0.1 to 3.0 percent by weight based on weight of main vehicle resin solids; i.e., the active hydrogen-containing cationic resin and capped polyisocyanate curing agent, preferably from
25 about 0.4 to 1.5 percent by weight based on weight of main vehicle resin solids.

 The electrodepositable composition may optionally contain a coalescing solvent such as hydrocarbons, alcohols, esters, ethers and ketones. Examples of preferred coalescing solvents
30 are alcohols, including polyols, such as isopropanol, butanol, 2-ethylhexanol, ethylene glycol and propylene glycol; ethers such as the monobutyl and monohexyl ethers of ethylene glycol;

- 14 -

and ketones such as methyl isobutyl ketone and isophorone. The coalescing solvent is usually present in an amount up to about 40 percent by weight, preferably ranging from about 0.05 to 25 percent by weight based on total weight of the electrodepositable composition.

The electrodepositable composition of the present invention may further contain pigments and various other optional additives such as plasticizers, surfactants, wetting agents, defoamers, and anti-cratering agents.

Examples of suitable surfactants and wetting agents include alkyl imidazolines such as those available from Geigy Industrial Chemicals as GEIGY AMINE C, and acetylenic alcohols available from Air Products and Chemicals as SURFYNOL. Examples of defoamers include a hydrocarbon containing inert diatomaceous earth available from Crucible Materials Corp. as FOAMKILL 63. Examples of anti-cratering agents are polyepoxide-polyoxyalkylene-polyamine reaction products such as those described in U.S. Patent No. 4,423,166. These optional ingredients, when present, are usually used in an amount up to 30 percent by weight, typically about 1 to 20 percent by weight based on weight of resin solids.

Suitable pigments include, for example, iron oxides, lead oxides, strontium chromate, carbon black, coal dust, titanium dioxide, talc, clay, silica, lead silicate, and barium sulfate, as well as color pigments such as cadmium yellow, cadmium red, chromium yellow, and the like. The pigment content of the aqueous dispersion, generally expressed as the pigment to resin (or pigment to binder) ratio (P/B) is usually about 0.05:1 to 1:1.

The composition of the present invention comprising the cationic resin, the capped polyisocyanate curing agent, the catalyst, the acid functional compound, and the optional

- 15 -

additives mentioned above is used in an electrodeposition process in the form of an aqueous dispersion. By "dispersion" is meant a two-phase transparent, translucent, or opaque aqueous resinous system in which the resin, pigment, and water insoluble materials are in the dispersed phase while water and water soluble materials comprise the continuous phase. The dispersed phase has an average particle size less than about 10 microns, preferably less than 5 microns. The aqueous dispersion preferably contains at least about 0.05 and usually about 0.05 to 50 percent by weight resin solids, depending on the particular end use of the dispersion.

Addition of the acid functional compound to the electrodepositable composition of the present invention improves the cure response of the composition when it is used in an electrocoating process. By this is meant that the temperature range for curing of the electrodepositable composition of the present invention may be about 310 to 325°F (154.5 to 162.7°C), as opposed to 325 to 340°F (162.7 to 171.1°C) for conventional electrodepositable compositions at conventional organotin catalyst levels; i.e., about 0.5 to 1.0 percent by weight tin based on weight of resin solids. The composition of the present invention also demonstrates improved cure response as measured by solvent resistance when cured at underbake temperatures (about 310°F, 154.5°C) compared to conventional electrodepositable compositions without the acid functional compound, once again at optimized organotin catalyst levels. Moreover, the cure rate is improved; i.e., at a given temperature, a deposited film of the present invention cures more quickly than a comparable film without the acid functional compound, as measured by rate of weight loss of a deposited film during baking. Alternatively, the amount of organotin catalyst can be reduced while maintaining cure at normal temperatures.

- 16 -

Addition of the acid functional compound to the electrodepositable composition of the present invention also improves the appearance of the composition when it is used in an electrocoating process. Cationic electrodeposition compositions are conventionally formulated with lead as either a pigment or a soluble lead salt. When these compositions also contain low levels of organotin catalysts; i.e., about 0.05 to 0.5 percent by weight tin based on weight of total resin solids, the cured deposited films exhibit a "fuzzy" or bristle-like appearance, particularly with aging of the electrodeposition bath. Addition of the acid functional compound to the electrodepositable composition in accordance with the present invention improves the appearance of cured electrodeposited films, eliminating the fuzzy appearance even with low levels of organotin catalyst in the composition.

Addition of the preferred acid functional compound, abietic acid, to the electrodepositable composition likewise improves cure and appearance, while maintaining the humidity and salt solution resistance of the composition when it is used as a coating over electrogalvanized substrate.

In the process of electrodeposition the aqueous dispersion is placed in contact with an electrically conductive anode and cathode. Upon passage of an electric current between the anode and cathode while they are in contact with the aqueous dispersion, an adherent film of the electrodepositable composition will deposit in a substantially continuous manner on the cathode. The film will contain the active hydrogen-containing resin, the capped polyisocyanate curing agent, the tin catalyst, the acid functional compound, and the optional additives from the non-aqueous phase of the dispersion. Electrodeposition is usually carried out at a constant voltage in the range of from about 1 volt to several thousand volts,

- 17 -

typically between 50 and 500 volts. Current density is usually between about 1.0 ampere and 15 amperes per square foot (10.8 to 161.5 amperes per square meter) and tends to decrease quickly during the electrodeposition process, indicating formation of a continuous self-insulating film. Any electroconductive substrate, especially metal substrates such as steel, zinc, aluminum, copper, magnesium or the like can be coated with the electrodepositable composition of the present invention. Steel substrates are preferred. It is customary to pretreat the substrate with a phosphate conversion, usually a zinc phosphate conversion coating, followed by a rinse which seals the conversion coating.

After deposition, the coating is heated to cure the deposited composition. The heating or curing operation is usually carried out at a temperature in the range of from 250 to 400°F (121.1 to 204.4°C), preferably from 300 to 340°F (148.8 to 171.1°C) for a period of time ranging from 10 to 60 minutes. The thickness of the resultant film is usually from about 10 to 50 microns.

The invention will be further described by reference to the following examples. Unless otherwise indicated, all parts and percentages are by weight.

Example I

Examples I-A to I-O illustrate the effect of adding various water immiscible acid functional compounds to a cationic electrodepositable composition in accordance with the present invention, compared to the effect of various non-acid functional compounds added to a cationic electrodepositable composition.

- 18 -

EXAMPLE I-A (Control)

This example describes the preparation of a cationic electrodeposition bath containing no additive. A main vehicle (i.e., the active hydrogen-containing cationic resin and capped polyisocyanate curing agent) was prepared from the following ingredients:

Ingredients	Parts by Weight
EPON 828 ¹	614.68
Bisphenol A-ethylene oxide adduct (1:6 molar ratio)	250.00
Bisphenol A	265.42
Methyl isobutyl ketone	59.48
Ethyltriphenyl phosphonium iodide	0.6
Crosslinker ²	682.85
Diketimine ³	56.01
N-methyl ethanolamine	48.68

¹Polyglycidyl ether of Bisphenol A, available from Shell Oil and Chemical Co.

²The capped polyisocyanate crosslinker was prepared from the following mixture of ingredients:

Ingredients	Parts by Weight
Polyisocyanate ^a	1325.00
Methyl isobutyl ketone (MIBK)	221.81
2-(2-Butoxyethoxy)ethanol	162.23
Dibutyltin dilaurate (DBTDL)	0.2
2-Butoxy ethanol	1063.62

^aMixture of diphenyl-4,4'-diisocyanate and polyphenyl polyisocyanate, available from Miles, Inc. as MONDUR MR.

The polyisocyanate, MIBK, and DBTDL were charged to a reaction flask under a nitrogen atmosphere. 2-(2-Butoxyethoxy)ethanol was added slowly allowing the reaction mixture to exotherm to a temperature between 45 and 50°C. Upon completion of the addition the reaction mixture was held at 50°C for 30 minutes.

- 19 -

2-Butoxy ethanol was then added and the mixture allowed to exotherm to 110°C and held there until infrared analysis indicated complete consumption of the isocyanate.

- 5 ³Diketimine derived from diethylene triamine and methyl isobutyl ketone (MIBK) (73% solids in MIBK)

A reaction vessel was charged with the EPON 828, Bisphenol A-ethylene oxide adduct, Bisphenol A and MIBK. This mixture was
10 heated under a nitrogen blanket to 125°C. Ethyl triphenylphosphonium iodide was then added and the reaction mixture allowed to exotherm to a temperature of about 145°C. The reaction was held at 145°C for two hours and the epoxy equivalent weight was determined. At this point, the
15 crosslinker, the diketimine, and N-methyl ethanolamine were added in succession. The reaction mixture exothermed and then a temperature of 132°C was established and maintained for an hour. The resin mixture (1684 parts) was dispersed in aqueous medium by adding it to a mixture of 38.34 parts sulfamic acid and
20 1220.99 parts deionized water. The dispersion was further thinned with 657.63 parts deionized water and 666.28 parts deionized water in stages and vacuum stripped to remove organic solvent to yield a dispersion having a solids content of 41.2 percent and a particle size of 984 Angstroms.

- 25 A cationic electrodeposition bath was prepared from the following ingredients:

Ingredients	Parts by Weight
Main vehicle prepared above	1395.8
Co-resin 1 ¹	168.2
Butyl CARBITOL formal plasticizer ²	27.1
Co-resin 2 ³	73.9
Deionized water	1943.7
E-6066 paste ⁴	191.3

- 20 -

- 1An aqueous dispersion of a flexibilizer-flow control agent generally in accordance with U.S. Patent No. 4,423,166 was prepared for use with the electrodepositable composition. The flexibilizer-flow control agent was prepared from a polyepoxide (EPON 828) and a polyoxyalkylene-polyamine (JEFFAMINE D-2000 from Texaco Chemical Co.). The flexibilizer-flow control agent was dispersed in aqueous medium with the aid of lactic acid and the dispersion had a resin solids content of 36.2%.
- 2The reaction product of 2 moles of diethylene glycol butyl ether and 1 mole of formaldehyde, prepared as generally described in U.S. Patent No. 4,891,111.
- 3A cationic microgel prepared as generally described in Examples A and B of U.S. Patent No. 5,096,556, with the exception that acetic acid instead of lactic acid was used to disperse the soap of Example A, ethylene glycol butyl ether instead of MIBK was used as a solvent in the soap of Example A, and EPON 828 solution was added after stripping rather than before in Example B. The resin had a final solids content of 18.3%.
- 4A pigment paste commercially available from PPG Industries Inc., containing 27.2% titanium dioxide, 1.4% carbon black, 15.9% aluminum silicate, 5.7% basic lead silicate, and 3.8% dibutyltin oxide.

Examples I-B to I-O

- Main vehicles and electrodeposition baths were prepared as generally described in Example I-A; however, various water immiscible acid functional compounds or non-acid functional compounds as reported in Table I below were added to the cationic main vehicle reaction mixture at 1% on main vehicle resin solids after the exotherm and one-hour hold at 132 °C described in the main vehicle preparation method above.
- The baths for the above examples including the control were ultrafiltered, removing 20% of the total weight of the bath as ultrafiltrate and replacing the ultrafiltrate with deionized water. Zinc phosphate pretreated steel panels were immersed in the baths and electrocoated with the electrodepositable compositions at 275 volts for 2 min. at a bath temperature of

- 21 -

87-95°F (30.5-35°C). After rinsing with deionized water, the panels were baked for 30 minutes at 310 °F (154.5°C), 325°F (162.7°C), or 340°F (171.1°C). Resulting film builds were about 0.9 mils (22.9 microns). The cured coatings were evaluated for appearance as measured by the surface profile (R_A) described below and for cure response as measured by acetone resistance and cure rate (TGA). The results are reported in Table I below.

Table I

Example	Additive	R_A ¹	Acetone Resistance ²	TGA ³
I-A (Control)	none	14.5	20	22
I-B	oleic acid	8.3	>100	77
I-C	9-11,9-12 octadecadienoic acid	7.3	>100	49
I-D	stearic acid	6.9	>100	88
I-E	linoleic acid	6.8	>100	64
I-F	linolenic acid	7.7	>100	88
I-G	12-hydroxy stearic acid	9.3	>100	36
I-H	lauric acid	11.5	>100	102
I-I	isodecanoic acid	9.8	>100	66
I-J	hexanoic acid	12.1	>100	83
I-K	isovaleric acid	18.4	>100	57
I-L	dimer fatty acid	8.2	>100	60
I-M (Comparative)	oleyl amine	6.7	13	35
I-N (Comparative)	oleyl alcohol	9.8	45	43
I-O (Comparative)	squalene	9.8	55	38

¹Data obtained from panels coated in baths aged two (2) weeks. Relative roughness of the coating surface is measured with a Surfalyzer, Model 21-9010-01, Federal Products, Inc. The number reported is the average roughness, or the average vertical distance of any point on the surface from a centerline determined by a stylus moving across the surface, expressed in micro-inches. Lower numbers indicate greater smoothness. These data were obtained from panels cured for 30 minutes at 340°F (171.1°C).

²An acetone saturated cloth was firmly rubbed back and forth across the cured coating surface. The number reported is the number of double rubs required to expose the metal surface. These data were obtained from panels cured for 30 minutes at 310°F (154.5°C).

Thermo-Gravimetric Analysis: The weight loss of a curing coating is monitored versus time for thirty (30) minutes at 325°F (162.7°C). The linear portion of the plot of the rate of change of the rate of weight loss versus time is recorded, expressed as percent weight loss per minute² times 10³ (% weight loss/min² x 10³). The higher the values, the faster the weight loss and the greater the cure rate.

The data in Table I indicate that all the acid-functional compounds tested tend to improve cure, while other long-chain materials and highly unsaturated materials do not significantly improve cure. As the total number of carbons in the hydrocarbon chain of the acid-functional compound increases, the appearance of the cured coating tends to improve.

Example II

The following examples (II-A to II-C) illustrate the effect of adding various levels of a water immiscible acid functional compound to a cationic electrodepositable composition in accordance with the present invention. The electrodeposition baths were prepared and zinc phosphate pretreated steel panels were coated and cured as in Example I. Results are reported in Table II below.

Table II

Example	Additive Amount ¹	R _A	Acetone Resistance	TGA
I-A (Control)	none	14.5	20	22
II-A	0.5% oleic acid	9.2	>100	52
I-B	1.0% oleic acid	8.3	>100	77
II-B	2.0% oleic acid	8.6	>100	113
II-C	3.0% oleic acid	9.2	>100	185

¹Amount reported is percent by weight based on main vehicle solids.

The data in Table II indicate that the effect of an acid functional compound on cure rate (TGA) is proportional to its level.

Example III

The following examples (III-A and III-B) illustrate the effect of adding a water immiscible acid functional compound to a cationic electrodepositable composition containing a polyisocyanate crosslinking agent capped with a "sluggish" capping agent; i.e., a capping agent such as a secondary alcohol which does not readily uncap at standard cure temperatures. The compositions were prepared as in Example I, with the following exception. The capped polyisocyanate crosslinker was prepared from the following mixture of ingredients:

Ingredients	Parts by Weight
Polyisocyanate ^a	1325.00
MIBK	193.39
Monomethyl ether of propylene glycol	901.2
DBTDL	0.2

^aMONDUR MR.

The polyisocyanate, MIBK, and DBTDL were charged to a reaction flask under a nitrogen atmosphere. The monomethyl ether of propylene glycol was added slowly allowing the reaction mixture to exotherm to a temperature between 100 and 110°C. Upon completion of the addition the reaction mixture was held at 110°C until infrared analysis indicated complete consumption of the isocyanate.

The crosslinker was incorporated into the electrodeposition bath as in Example I-A, except at 31% solids on solids instead of at 34% solids on solids.

The electrodepositable composition of Example III-A contained no acid functional materials, while that of Example III-B contained 1% oleic acid by weight, based on weight of main

vehicle resin solids. The electrodeposition baths were prepared and zinc phosphate pretreated steel panels were coated and cured as in Example I unless otherwise indicated. Results are reported in Table III below.

5

Table III

Example	Additive Amount	R _A	Acetone Resistance 310°F ¹	Acetone Resistance 340°F ²	TGA ³ 325°F	TGA ⁴ 340°F
III-A (control)	none	6.7	1	45	28	55
III-B	1.0%	6.1	95	>100	38	125

¹These data were obtained from coated panels cured for 30 minutes at 310°F (154.5°C).

10

²These data were obtained from coated panels cured for 30 minutes at 340°F (171.1°C).

³These data were obtained from coated panels cured for 30 minutes at 325°F (162.7°C).

15

⁴These data were obtained from coated panels cured for 30 minutes at 340°F (171.1°C).

20

The data in Table III indicate that acid functional compounds improve the cure rate (TGA) in a system containing a polyisocyanate crosslinking agent capped with a "sluggish" capping agent. Acetone resistance and appearance are also improved.

25

Example IV

The following examples (IV-A and IV-B) illustrate the effect of adding water immiscible acid functional compound to a cationic electrodepositable composition containing dioctyltin oxide instead of dibutyltin oxide, at equal tin levels, as the catalyst.

30

- 25 -

Example IV-A

This example demonstrates the preparation of a cationic electrodepositable composition containing dioctyltin oxide catalyst and no acid functional compound.

5

A pigment paste was prepared from the following ingredients:

Ingredients	Parts by Weight
Pigment grinding vehicle ¹	338.0
Deionized water	507.1
Titanium dioxide ²	564.0
Aluminum silicate ³	330.0
Carbon Black ⁴	28.0
Basic lead silicate ⁵	118.0
Dioctyltin oxide	114.9

10 ¹The pigment grinding vehicle was prepared by first preparing a quaternizing agent followed by reacting the quaternizing agent with an epoxy resin. The quaternizing agent was prepared as follows:

Ingredients	Solution weight (grams)	Solid weight
2-Ethylhexanol half-capped toluene diisocyanate in MIBK	320	304
Dimethylethanolamine (DMEA)	87.2	87.2
Aqueous lactic acid solution	117.6	58.2
2-Butoxyethanol	39.2	---

15 The 2-ethylhexanol half-capped toluene diisocyanate was added to the DMEA in a suitable reaction vessel at room temperature. The mixture exothermed and was stirred for one hour at 80°C. The aqueous lactic acid solution was then charged followed by the addition of 2-butoxyethanol. The reaction mixture was stirred for about one hour at 65°C to form the quaternizing agent.

20

- 26 -

The pigment grinding vehicle was prepared as follows:

Ingredients	Solution weight (grams)	Solid weight
EPON 829 ^a	710	682
Bisphenol A	289.6	289.6
2-Ethylhexanol half-capped toluene diisocyanate in MIBK	406	386.1
Quaternizing agent described above	496.3	421.9
Deionized water	71.2	---
2-Butoxyethanol	1490	---

^aDiglycidyl ether of Bisphenol A available from Shell Oil and Chemical Co.

5

The EPON 829 and Bisphenol A were charged under a nitrogen atmosphere to a suitable reactor and heated to 150 to 160°C to initiate an exotherm. The reaction mixture was permitted to exotherm for one hour at 150 to 160°C. The reaction mixture was then cooled to 120°C and the 2-ethylhexanol half-capped toluene diisocyanate added. The temperature of the reaction mixture was held at 110 to 120°C for one hour followed by the addition of the 2-butoxyethanol. The reaction mixture was then cooled to 85 to 90°C, homogenized and charged with water followed by the quaternizing agent. The temperature of the reaction mixture was held at 80 to 85°C until an acid value of about 1 was obtained. The final product had a solids content of about 57.1%.

²Available from E. I. Du Pont de Nemours and Co. as R-900.

20

³Available from Engelhard Corp. as ASP-200.

⁴Available from the Columbian division of Cities Service Co. as Raven 410.

25

⁵Available from Eagle-Picher Industries, Inc. as EP202.

The pigment paste was sand milled to a Hegman reading of 7.

A cationic electrodeposition bath was prepared from the following ingredients:

30

- 27 -

Ingredients	Parts by Weight
Main vehicle of Example I-A	1456.5
Co-resin 1 of Example I-A	178.0
Butyl CARBITOL formal plasticizer	28.2
Co-resin 2 of Example I-A	77.6
Deionized water	1865.6
Pigment paste described above	194.1

Example IV-B

This example demonstrates the preparation of a cationic electrodepositable composition containing dioctyltin oxide catalyst and a water immiscible acid functional compound at 1 weight percent on main vehicle solids.

A cationic electrodeposition bath was prepared from the following ingredients:

10

Ingredients	Parts by Weight
Main vehicle of Example I-A	971.0
Main vehicle of Example II-C	454.2
Co-resin 1 of Example I-A	178.0
Butyl CARBITOL formal plasticizer	28.2
Co-resin 2 of Example I-A	77.6
Deionized water	1896.9
Pigment paste of Example IV-A	194.1

The electrodeposition baths of Examples IV-A and IV-B were prepared and zinc phosphate pretreated steel panels were coated and cured as in Example I. Results are reported in Table IV below.

15

- 28 -

Table IV

Example	Additive Amount	R _A	Acetone Resistance	TGA
IV-A (Control)	none	9.8	>100 (coating softened)	56
IV-B	1.0% oleic acid	9.7	>100 (no softening)	147

The data in Table IV indicate that addition of a water immiscible acid functional compound to a cationic electrodepositable composition containing dioctyltin oxide clearly improves the cure rate, as shown by the marked increase in TGA.

Example V

The following examples (V-A and V-B) illustrate the effect of reacting a water immiscible acid functional compound into the main vehicle at 1% on main vehicle solids, forming an epoxy ester, compared to post-adding the acid functional compound to the cationic electrodepositable composition.

EXAMPLE V-A

This example describes the preparation of a cationic electrodeposition bath containing 1% oleic acid on main vehicle solids, post-added to the fully reacted resin. A main vehicle was prepared from the following ingredients:

Ingredients	Parts by Weight
EPON 828	1844.03
Bisphenol A-ethylene oxide adduct (1:6 molar ratio)	75.00
Bisphenol A	796.27
Methyl isobutyl ketone	69.19
Ethyltriphenyl phosphonium iodide	1.80

EXAMPLE V-A (Cont'd)

Ingredients	Parts by Weight
Bisphenol A-ethylene oxide adduct (1:6 molar ratio)	675.00
Methyl isobutyl ketone	10.98
Crosslinker of Example I-A	2049.23
Diketimine of Example I-A	168.02
N-methyl ethanolamine	146.03

A reaction vessel was charged with the EPON 828, the initial charge of Bisphenol A-ethylene oxide adduct, Bisphenol A and the initial charge of MIBK. This mixture was heated under a nitrogen blanket to 125°C. Ethyl triphenylphosphonium iodide was then added and the reaction mixture allowed to exotherm to a temperature of about 145°C. The reaction was held at 145 °C for two hours and the second charge of Bisphenol A-ethylene oxide adduct was added and the epoxy equivalent weight was determined. At this point, the second charge of MIBK, the crosslinker, the diketimine, and N-methyl ethanolamine were added in succession. The reaction mixture exothermed and then a temperature of 132°C was established and maintained for an hour. The resin mixture (1500 parts) was dispersed in aqueous medium by adding it to a mixture of 34.72 parts sulfamic acid and 1145.23 parts deionized water. After five minutes 14.25 parts oleic acid was added to the high solids dispersion and further mixed for 30 minutes. The dispersion was further thinned with 581.29 parts deionized water and 603.38 parts deionized water in stages and vacuum stripped to remove organic solvent to yield a dispersion having a solids content of 42.6 percent and a particle size of 861 Angstroms.

A cationic electrodeposition bath was prepared from the following ingredients:

- 30 -

Ingredients	Parts by Weight
Main vehicle prepared above	1349.9
Co-resin 1 of Example I-A	168.2
Butyl CARBITOL formal plasticizer	27.1
Co-resin 2 of Example I-A	73.9
Deionized water	1989.6
E-6066 paste	191.3

EXAMPLE V-B

This example describes the preparation of a cationic electrodeposition bath containing 1% oleic acid on main vehicle solids, reacted into the resin during the epoxy extension stage. A main vehicle was prepared from the following ingredients:

Ingredients	Parts by Weight
EPON 828	614.68
Bisphenol A-ethylene oxide adduct (1:6 molar ratio)	250.00
Bisphenol A	265.42
Methyl isobutyl ketone	60.45
Ethyltriphenyl phosphonium iodide	0.6
Oleic acid	18.48
Crosslinker of Example I-A	683.08
Diketimine of Example I-A	56.56
N-methyl ethanolamine	48.68

10 A reaction vessel was charged with the EPON 828, Bisphenol A-ethylene oxide adduct, Bisphenol A, oleic acid, and the MIBK. This mixture was heated under a nitrogen blanket to 125°C. Ethyl triphenylphosphonium iodide was then added and the reaction mixture allowed to exotherm to a temperature of about
 15 145°C. The reaction was held at 145°C for two hours and the epoxy equivalent weight was determined. At this point, the crosslinker, the diketimine, and N-methyl ethanolamine were added in succession. The reaction mixture exothermed and then a

- 31 -

temperature of 132°C was established and maintained for an hour. The resin mixture (1700 parts) was dispersed in aqueous medium by adding it to a mixture of 38.31 parts sulfamic acid and 1219.38 parts deionized water. The dispersion was further
5 thinned with 657.26 parts deionized water and 665.91 parts deionized water in stages and vacuum stripped to remove organic solvent to yield a dispersion having a solids content of 43.1 percent and a particle size of 870 Angstroms.

A cationic electrodeposition bath was prepared as in
10 Example V-A except that the main vehicle of Example V-B was used in place of the main vehicle of Example V-A.

The electrodeposition baths of Examples V-A and V-B were prepared and zinc phosphate pretreated steel panels were coated and cured as in Example I. Results are reported in Table V
15 below.

Table V

Example	Additive Amount	R _A	Acetone Resistance	TGA
V-A	1.0% oleic acid (post-add)	9.0	>100	77
V-B	1.0% oleic acid (reacted in)	10.6	30	25

The data in Table V indicate that post-addition of a water
20 immiscible acid functional compound to the cationic electrodepositable composition of Example V provides better appearance, cure, and cure rate than does reaction of the cationic resin with the water immiscible acid functional compound.

25

- 32 -

Example VI

The following examples (VI-A to VI-G) illustrate the effect of adding a water immiscible acid functional compound to the cationic electrodepositable composition with respect to the levels of tin catalyst required for appearance and cure.

EXAMPLE VI-A

This example describes the preparation of a cationic electrodeposition bath containing 1.45% dibutyltin oxide (DBTO) on total resin solids (0.69% tin on total resin solids), and no water immiscible acid functional compound.

A pigment paste was prepared from the following ingredients:

Ingredients	Parts by Weight
Pigment grinding vehicle of Example IV-A	1515.5
Deionized water	2659.0
Titanium dioxide	2712.5
Aluminum silicate	1582.5
Carbon Black	134.5
Basic lead silicate	570.5

The paste was sand milled to a Hegman reading of 7.

A catalyst paste was prepared from the following ingredients:

Ingredients	Parts by Weight
Pigment grinding vehicle of Example IV-A	137.9
Dibutyltin oxide	200
Deionized water	268.2

The paste was sand milled to a Hegman reading of 7.

- 33 -

A cationic electrodeposition bath was prepared from the following ingredients:

Ingredients	Parts by Weight
Main vehicle of Example I-A	1391.1
Co-resin 1 of Example I-A	168.2
Butyl CARBITOL formal plasticizer	27.1
Co-resin 2 of Example I-A	73.9
Deionized water	1934.7
Pigment paste described above	172.4
Catalyst paste described above	32.6

EXAMPLE VI-B

- 5 This example describes the preparation of a cationic electrodeposition bath containing 1.45% DBTO on total resin solids (0.69% tin on total resin solids), and 1% water immiscible acid functional compound on main vehicle solids.

- 10 A cationic electrodeposition bath was prepared from the following ingredients:

Ingredients	Parts by Weight
Main vehicle of Example V-A	5379.5
Co-resin 1 of Example I-A	670.3
Butyl CARBITOL formal plasticizer	107.8
Co-resin 2 of Example I-A	294.7
Deionized water	7928.0
Pigment paste of Example VI-A	689.5
Catalyst paste of Example VI-A	130.2

EXAMPLE VI-C to VI-G

- 15 These examples describe the preparation of various cationic electrodeposition baths containing reduced levels of DBTO and 1% acid functional compound on main vehicle solids. The baths were prepared by diluting the bath of Example VI-B,

- 34 -

containing 1.45% DBTO on total resin solids, with a bath containing no DBTO, prepared from the following ingredients:

Ingredients	Parts by Weight
Main vehicle of Example V-A	4049.8
Co-resin 1 of Example I-A	504.6
Butyl CARBITOL formal plasticizer	81.2
Co-resin 2 of Example I-A	221.8
Deionized water	5970.2
Pigment paste of Example VI-A	572.4

Example	Parts by weight (Bath of Example VI-B)	Parts by weight (DBTO-free Bath)	% DBTO (tin) on total resin solids
VI-C	2830.0	970.0	1.08 (0.515)
VI-D	2359.0	1441.0	0.9 (0.429)
VI-E	1835.0	1965.0	0.7 (0.334)
VI-F	1310.0	2490.0	0.5 (0.238)
VI-G	786.0	3014.0	0.3 (0.143)

The electrodeposition baths of Examples VI-A to VI-G were prepared and zinc phosphate pretreated steel panels were coated and cured as in Example I. Results are reported in Table VI below.

Table VI

Example	Additive Amount (oleic acid)	% DBTO (tin) on total resin solids	R _A	Acetone Resistance	TGA
VI-A	0	1.45 (0.691)	10.7	>100 (extremely soft)	32
VI-B	1.0%	1.45 (0.691)	6.8	>100 (very slightly soft)	170
VI-C	1.0%	1.08 (0.515)	7.7	>100 (soft)	122
VI-D	1.0%	0.9 (0.429)	7.4	>100 (very soft)	82

Table VI (Cont'd)

Example	Additive Amount (oleic acid)	% DBTO (tin) on total resin solids	R _A	Acetone Resistance	TGA
VI-E	1.0%	0.7 (0.334)	8.6	>100 (extremely soft)	63
VI-F	1.0%	0.5 (0.238)	9.8	75	43
VI-G	1.0%	0.3 (0.143)	9.4	40	27

The data in Table VI indicate that the appearance of a coating is improved when the composition contains a water immiscible acid functional compound, for all levels of catalyst tested. Cure, as measured by acetone resistance, is equal for the composition containing 0.7% DBTO with a water immiscible acid functional compound and the composition containing 1.45% DBTO with no acid functional compound. Cure rate as measured by TGA is slightly better for a composition containing 0.5% DBTO with a water immiscible acid functional compound than the composition containing 1.45% DBTO with no water immiscible acid functional compound.

Example VII

The following examples (VII-A and VII-B) illustrate the effect of adding a water immiscible acid functional compound to a lead-free cationic electrodepositable primer composition.

EXAMPLE VII-A

This example describes the preparation of a cationic electrodeposition primer bath containing no lead and no water immiscible acid functional compound.

- 36 -

A pigment paste was prepared from the following ingredients:

Ingredients	Parts by Weight
Pigment grinding vehicle of Example IV-A	1167.8
Deionized water	2011.8
Aluminum silicate	2449.6
Carbon Black	1428.8
Titanium dioxide	121.6

- 5 The pigment paste was sand milled to a Hegman reading of 7.

A cationic electrodeposition bath was prepared from the following ingredients:

Ingredients	Parts by Weight
Main vehicle of Example I-A	1462.5
Co-resin 1 of Example I-A	178.7
Butyl CARBITOL formal plasticizer	28.4
Co-resin 2 of Example I-A	77.1
Deionized water	1857.7
Pigment paste described above	195.6
Catalyst paste of Example IV-A	23.8

10

EXAMPLE VII-B

This example describes the preparation of a cationic electrodeposition primer bath containing no lead and 1% water immiscible acid functional compound on main vehicle solids.

- 15 A cationic electrodeposition bath was prepared from the following ingredients:

- 37 -

Ingredients	Parts by Weight
Main vehicle of Example V-A	1414.3
Co-resin 1 of Example I-A	178.7
Butyl CARBITOL formal plasticizer	28.4
Co-resin 2 of Example I-A	77.1
Deionized water	1905.9
Pigment paste of Example VII-A	195.6
Catalyst paste of Example IV-A	23.8

The electrodeposition baths of Examples VII-A and VII-B were prepared and zinc phosphate pretreated steel panels were coated and cured as in Example I. Results are reported in Table VII below.

Table VII

Example	Additive Amount	R_A^1	Acetone Resistance ²	TGA ³ 325°F	TGA ⁴ 340°F
VII-A (control)	none	5.61	5	13	48
VII-B	1.0%	8.45	>100	119	315

¹These data were obtained from coated panels cured for 30 minutes at 340°F (171.1°C).

²These data were obtained from coated panels cured for 30 minutes at 310°F (154.5°C).

³These data were obtained from coated panels cured for 30 minutes at 325°F (162.7°C).

⁴These data were obtained from coated panels cured for 30 minutes at 340°F (171.1°C).

The data in Table VII indicate that addition of water immiscible acid functional compounds to lead-free electrodepositable compositions improve the cure as measured by

- 38 -

acetone resistance and TGA, despite the absence of lead as an auxiliary isocyanate decapping catalyst.

EXAMPLE VIII

- 5 This example illustrates gum rosin or natural abietic acid as the water immiscible acid functional compound having a hydrocarbon chain of at least 5 carbon atoms. The gum rosin has several unexpected advantages over oleic acid, and that 0.3% abietic acid on main vehicle solids is similar or improved over
10 0.5% oleic acid on main vehicle solids in all properties.

EXAMPLE VIII-A

This example describes the preparation of a cationic electrodeposition bath containing no additives.

- 15 A main vehicle was prepared from the following ingredients.

Ingredients	Parts by weight
EPON 828	2415.68
Bisphenol A-ethylene oxide adduct (1/6 molar ratio)	98.25
Bisphenol A	1043.11
Methyl isobutyl ketone	90.63
Ethyltriphenyl phosphonium iodide	2.36
Bisphenol A-ethylene oxide adduct (1/6 molar ratio)	884.25
Methyl isobutyl ketone	328.31
Crosslinker ¹	2736.09
Diketimine ²	224.04
N-methyl ethanol amine	191.3

- ¹The capped polyisocyanate crosslinker was prepared from the
20 following mixture of ingredients:

- 39 -

Ingredients	Parts by weight
Polyisocyanate ^a	1325.00
Methyl isobutyl ketone	221.81
2-(2-Butoxyethoxy)ethanol	324.46
Dibutyltin dilaurate	0.2
2-Butoxy ethanol	945.44

^aPolymeric MDI available from Miles Inc. as MONDUR MR as noted in Example 1-A.

- 5 The polyisocyanate, methyl isobutyl ketone and dibutyltin dilaurate were charged to a reaction flask under a nitrogen atmosphere. 2-(2-butoxyethoxy)ethanol was added slowly allowing the reaction to exotherm to a temperature between 45 to 50°C.
- 10 Upon completion of the addition the reaction mixture was held at 50°C for 30 minutes. 2-butoxy ethanol then was added and the mixture allowed to exotherm 110°C and held there until Infrared analysis indicated no unreacted NCO remained.

- 15 ²Diketimine derived from diethylenetriamine and methyl isobutyl ketone (73% solids in methyl isobutyl ketone).

- The EPON 828, initial charge of Bisphenol A-ethylene oxide adduct, Bisphenol A and the initial charge of methyl isobutyl ketone were charged to a reaction vessel and heated under a nitrogen atmosphere to 125°C. Ethyl triphenyl phosphonium iodide then was added and the reaction mixture allowed to exotherm to about 145°C. The reaction was held at 145°C for 2 hours and the second charge of Bisphenol A-ethylene oxide adduct
- 25 was added and an epoxy equivalent was obtained. Epoxy equivalent usually stalls close to the target epoxy equivalent weight. At this point, the second charge of methyl isobutyl ketone, the crosslinker, the diketimine and N-methylethanolamine were added in succession. The mixture was allowed to exotherm
- 30 and then a temperature of 125°C was established. The mixture was held at 125°C for 1 hour. The resin mixture (7500 parts) was dispersed in aqueous medium by adding it to a mixture of

- 40 -

165.59 parts of sulfamic acid and 4908.21 parts of deionized water. After 60 minutes, the dispersion was further thinned with 2794.18 parts of deionized water and 2830.95 parts of deionized water in stages and vacuum stripped to remove organic solvent to give a dispersion having a solids content of 42.53 percent and a particle size of 830 Angstroms.

A cationic electrodeposition bath was prepared from the following ingredients:

Ingredients	Parts by weight
Main vehicle prepared above	1329.2
Co-resin 1 of Example IA, at 35.3% solids	170.6
Butyl CARBITOL formal plasticizer	37.2
Co-resin 2 of Example IA, at 18.4% solids	73.5
Deionized water	1990.1
E6066 paste	193.4
Total	3800.0

EXAMPLE VIII-B

This example describes the preparation of a cationic electrodeposition bath containing 0.5% oleic acid on main vehicle solids.

A main vehicle was prepared from the following ingredients.

Ingredients	Parts by weight
EPON 828	614.68
Bisphenol A-ethylene oxide adduct (1/6 molar ratio)	125.00
Bisphenol A	265.42
Methyl isobutyl ketone	20.51
Ethyltriphenyl phosphonium iodide	0.6
Bisphenol A-ethylene oxide adduct (1/6 molar ratio)	125.00
Methyl isobutyl ketone	87.22

- 41 -

EXAMPLE VIII-B (Cont'd)

Ingredients	Parts by weight
Crosslinker of Example VIII-A	693.55
Diketimine	54.99
N-methyl ethanol amine	46.96

The reaction was performed as in Example VIII-A, except
5 that after the second exotherm a temperature of 130°C was
established. The mixture was held at 130°C for 1 hour. The
resin mixture (1600 parts) was dispersed in aqueous medium by
adding it to a mixture of 34.17 parts of sulfamic acid and
1052.03 parts of deionized water. After 60 minutes, 7.20 parts
10 of Emersol 210 oleic acid (a commercial grade of oleic acid
available from Emery Chemicals Group of Henkel Corporation) was
added to the high solids dispersion and further mixed for 30
minutes. The dispersion was further thinned with 598.53 parts
of deionized water and 606.41 parts of deionized water in stages
15 and vacuum stripped to remove organic solvent to give a
dispersion having a solids content of 43.0 percent and a
particle size of 948 Angstroms.

A cationic electrodeposition bath was prepared from the
20 following ingredients:

Ingredients	Parts by weight
Main vehicle prepared above	2627.5
Co-resin 1 of Example IA at 35.3% solids	341.6
Butyl CARBITOL formal plasticizer	74.4
Co-resin 2 of Example IA at 18.4% solids	147.0
Deionized water	4022.7
E6066 paste	386.8
Total	7600.0

EXAMPLE VIII-C

This example describes the preparation of a cationic electrodeposition bath containing 0.5% of gum rosin (natural abietic acid) on main vehicle solids.

A main vehicle was prepared from the following ingredients:

Ingredients	Parts by weight
EPON 828	106.2
Bisphenol A-ethylene oxide adduct (1/6 molar ratio)	21.6
Bisphenol A	45.9
Methyl isobutyl ketone	5.4
Ethyltriphenyl phosphonium iodide	0.1
Bisphenol A-ethylene oxide adduct (1/6 molar ratio)	21.6
Methyl isobutyl ketone	13.0
Crosslinker of Example VIII-A	120.3
Diketimine	9.8
N-methyl ethanol amine	8.4

The reaction was performed as in Example VIII-A, except that after the second exotherm a temperature of 130°C was established. The mixture was held at 130°C for 1 hour. The resin mixture (345.3 parts) was dispersed in aqueous medium by adding it to a mixture of 7.62 parts of sulfamic acid and 227.2 parts of deionized water. After 60 minutes 1.6 parts of Gum Rosin available from the Colyer Chemical Company and 1.6 parts of methyl isobutyl ketone premixed was added as a solution to the high solids dispersion and further mixed for 30 minutes. This gum rosin contains 10% neutral materials and 90% rosin acid of which 90% is abietic acid (and isomers) and 10% is a mixture of dihydroabietic acid and dehydroabietic acid. The dispersion was further thinned with 129.3 parts of deionized water and 109.4 parts of deionized water in stages and vacuum stripped to

- 43 -

remove organic solvent to give a dispersion having a solids content of 40.8 percent and a particle size of 924 Angstroms.

A cationic electrodeposition bath was prepared from the following ingredients:

Ingredients	Parts by weight
Main vehicle prepared above	2769.2
Co-resin 1 of Example IA at 35.3% solids	341.6
Butyl CARBITOL formal	74.4
Co-resin 2 of Example IA at 18.4% solids	147.0
Deionized water	3881.4
E6066 paste	386.8
Total	7600.0

EXAMPLE VIII-D

This example describes the preparation of a cationic electrodeposition bath containing 0.3% of gum rosin (natural abietic acid) on main vehicle solids.

A main vehicle dispersion was prepared as in Example VIII-C, having a solids content of 41.3 percent and a particle size of 932 Angstroms. The dispersion differed from that of Example VIII-C in that it contained 0.3% gum rosin on main vehicle solids instead of 0.5%.

A cationic electrodeposition bath was prepared from the following ingredients:

Ingredients	Parts by weight
Main vehicle prepared above	2735.7
Co-resin 1 of Example IA at 35.3% solids	341.6
Butyl CARBITOL formal plasticizer	74.4
Co-resin 2 of Example IA at 18.4% solids	147.0
Deionized water	3914.9
E6066 paste	386.8
Total	7600.0

- 44 -

The baths of Examples VIII-A through VIII-D were each ultrafiltered, removing 20% of the total weight of the bath as ultrafiltrate and replacing the ultrafiltrate with deionized water. Smooth zinc phosphated steel panels and smooth unphosphated electrogalvanized steel panels were electrocoated with each composition at 275 volts for 2 minutes at bath temperatures of 81-86°F (27.2-30.0°C). After rinsing with deionized water, the panels were baked for 30 minutes at 310°F (154.5°C), 325°F (162.7°C), or 340°F (171.1°C). Resulting film builds were about 0.9 mils (22.9 microns). The cured coatings were measured for appearance, cure response as measured by acetone resistance and Thermo-Gravimetric Analysis (TGA), humidity resistance over electrogalvanized substrate, and resistance to warm salt solution over electrogalvanized substrate.

All test results are summarized on Table VIII.

TABLE VIII

Example	Additive	Wet Substrate Rupture Rating ¹	R _A ²	Acetone Resistance ³	TGA ⁴	Humidity Resistance ⁵		Warm Salt Solution Resistance ⁶	
						325°F	340°F	325°F	340°F
VIII-A	None	10	10.40	12	105	10	10	5mm.	5mm.
VIII-B	0.5% oleic acid	6	8.10	>100 (softens)	238	0	0	complete adhesion loss	complete adhesion loss
VIII-C	0.5% gum rosin	7.5	7.21	>100 (very slightly softens)	334	10	10	5mm.	4mm.
VIII-D	0.3% gum rosin	9	7.28	>100 (softens)	252	7	10	3.5mm.	3.5mm.

TABLE VIII (Footnotes)

- ¹Prior to ultrafiltration, the baths of Examples VIII-A through VIII-D were tested for resistance to rupturing defects over wet substrates in the following manner: A smooth zinc phosphated steel panel is prewet with deionized water then quickly electrocoated with 300 volts for 35 seconds at 95°F (35°C). The electrocoated panel is baked 30 minutes at 340°F (171°C) and observations are made of a tendency to produce swirling, ruptured, and raised defect areas. The rupturing patterns are rated on a scale of 0 to 10, 10 being best.
- ²These data were obtained from coated, zinc phosphated steel panels cured for 30 minutes at 340°F (171.1°C).
- ³These data were obtained from coated, zinc phosphated steel panels cured for 30 minutes at 310°F (154.5°C).
- ⁴These data were obtained from coated, zinc phosphated steel panels cured at 340°F (171.1°C).
- ⁵Panels on bare electrogalvanized steel, baked at 325°F (162.8°C) and 350°F (176.7°C), are exposed to condensing humidity from a bath maintained at 140°F (60°C), in a QCT cabinet supplied by Q-Panel Co., for 24 hours. They are immediately subjected to a cross-hatch adhesion test using a tool with 6 teeth 2mm. apart. They are then rated for adhesion loss on a scale of 0 = worst to 10 = best.
- ⁶X-scribed panels on bare electrogalvanized steel baked at 325°F (162.8°C) and 350°F (176.7°C) were soaked in 5% NaCl solution at 55°C for 120 hours. The panels were removed and rinsed with water. A knife was used to scrape off loosely adhering paint from around the scribe. The total width of scribe loss is measured and recorded at the widest point.

Example VIII demonstrates that in the electrodepositable composition of the present invention, abietic acid or gum rosin is significantly better than oleic acid for preventing rupturing on wet substrates, and for improving adhesion to bare electrogalvanized substrate, and is the preferred embodiment of the invention with respect to these properties. Gum rosin is slightly better than oleic acid for appearance and cure response. The example also demonstrates that 0.3% gum rosin on

- 47 -

main vehicle solids has effects on cure response approximately equivalent to 0.5% oleic acid, while providing a further improvement in resistance to rupturing defects over wet substrate.

5

WE CLAIM:

1. In a method of electrocoating an electroconductive substrate which serves as a cathode in an electrical circuit comprising said cathode and an anode immersed in an aqueous electrodepositable composition containing a cationic water dispersible resin, said method comprising passing an electric current between the anode and the cathode to cause the electrodepositable composition to deposit on the cathode as a substantially continuous film, and heating the electrodeposited film at an elevated temperature to cure the film, wherein the electrodepositable composition comprises (a) an active hydrogen-containing cationic resin electrodepositable on a cathode; (b) a capped polyisocyanate curing agent; and (c) an organotin-containing catalyst; the improvement comprising the addition to the electrodepositable composition of at least one water immiscible acid functional compound having a hydrocarbon chain of at least 5 carbon atoms selected from the group consisting of abietic acid and natural sources of abietic acid.
2. The method of claim 1 in which the cationic resin is derived from a polyepoxide.
3. The method of claim 1 wherein the cathode is a steel substrate.
4. The method of claim 2 in which the polyepoxide is a polyglycidyl ether of a polyhydric alcohol.
5. The method of claim 2 in which the cationic resin contains salt groups which are amine salt groups.

- 49 -

6. The method of claim 5 in which the amine salt groups are derived from basic nitrogen groups neutralized with an acid selected from the group consisting of formic acid, acetic acid, lactic acid, phosphoric acid, sulfamic acid, and mixtures thereof.

7. The method of claim 1 in which the acid functional compound is gum rosin.

8. The method of claim 1 in which the acid functional compound is a carboxylic acid.

9. The method of claim 1 in which the acid functional compound is polycyclic.

10. The method of claim 9 in which the acid functional compound is abietic acid.

11. The method of claim 1 in which the organotin-containing catalyst is present in amounts of about 0.05 to 1 percent tin by weight, based on the total weight of resin solids in the electrodepositable composition.

12. The method of claim 1 wherein the electrodepositable composition contains lead.

13. The method of claim 1 in which the electrodeposited film is heated to a temperature range of about 300 to 340°F (148.8 to 171.1°C) to cure the film.

14. The method of claim 1 wherein the addition of acid functional compound is in an amount ranging from about 0.1 to

- 50 -

3.0 percent by weight based on the weight of the main vehicle resin solids of the active hydrogen-containing cationic resin and the capped polyisocyanate curing agent.

5 15. The method of claim 14 wherein the acid functional compound is present in an amount ranging from about 0.4 to 1.5 percent by weight based on the weight of the main vehicle resin solids so that a reduced amount of the organotin-containing catalyst is present in amounts of about 0.05 to 0.5 percent tin
10 by weight, based on weight of resin solids.

16. The method of claim 1 wherein the acid functional compound is present from the addition of the acid functional compound to the electrodepositable composition and wherein the
15 acid functional compound remains unreacted with the cationic resin backbone of the active hydrogen-containing cationic resin in the electrodepositable composition to enable the acid functional compound to enhance the cure response when the organotin catalyst activates cure of the electrodeposition
20 composition.

17. The method of claim 1 wherein the polyisocyanate curing agent is present in the amount ranging from about 5 to 60 percent by weight based on total weight of resin solids.
25

18. The method of claim 17 wherein the polyisocyanate curing agent is present in the amount ranging from about 25 to 50 percent by weight based on total weight of resin solids.

30 19. In an electrodepositable composition comprising
(a) an active hydrogen-containing cationic resin electrodepositable on a cathode; (b) a capped polyisocyanate

- 51 -

curing agent; and (c) an organotin-containing catalyst; the improvement comprising the presence in the electrodepositable composition of at least one water immiscible acid functional compound having a hydrocarbon chain of at least 5 carbon atoms including abietic acid and natural sources thereof.

20. The electrodepositable composition of claim 19 in which the cationic resin is derived from a polyepoxide.

10 21. The electrodepositable composition of claim 20 in which the polyepoxide is a polyglycidyl ether of a polyhydric alcohol.

22. The electrodepositable composition of claim 20 in which the cationic resin contains salt groups which are amine salt groups.

23. The electrodepositable composition of claim 22 in which the amine salt groups are derived from basic nitrogen groups neutralized with an acid selected from the group consisting of formic acid, acetic acid, lactic acid, phosphoric acid, sulfamic acid, and mixtures thereof.

24. The electrodepositable composition of claim 19 in which the acid functional compound is a monocarboxylic acid.

25. The electrodepositable composition of claim 19 in which the acid functional compound is polycyclic.

30 26. The electrodepositable composition of claim 1 in which the organotin-containing catalyst is present in amounts of

- 52 -

about 0.05 to 1 percent tin by weight, based on the total weight of resin solids in the electrodepositable composition.

27. The electrodepositable composition of claim 26
5 further comprising lead.

28. The electrodepositable composition of claim 19 which
is curable at a temperature range of about 300 to 340°F (148.8
to 171.1°C).

10

AMENDED CLAIMS

[received by the International Bureau on 09 February 1998 (09.02.98); original claim 19 amended ; remaining claims unchanged (2 pages)]

3.0 percent by weight based on the weight of the main vehicle resin solids of the active hydrogen-containing cationic resin and the capped polyisocyanate curing agent.

5 15. The method of claim 14 wherein the acid functional compound is present in an amount ranging from about 0.4 to 1.5 percent by weight based on the weight of the main vehicle resin solids so that a reduced amount of the organotin-containing catalyst is present in amounts of about 0.05 to 0.5 percent tin
10 by weight, based on weight of resin solids.

16. The method of claim 1 wherein the acid functional compound is present from the addition of the acid functional compound to the electrodepositable composition and wherein the
15 acid functional compound remains unreacted with the cationic resin backbone of the active hydrogen-containing cationic resin in the electrodepositable composition to enable the acid functional compound to enhance the cure response when the organotin catalyst activates cure of the electrodeposition
20 composition.

17. The method of claim 1 wherein the polyisocyanate curing agent is present in the amount ranging from about 5 to 60 percent by weight based on total weight of resin solids.
25

18. The method of claim 17 wherein the polyisocyanate curing agent is present in the amount ranging from about 25 to 50 percent by weight based on total weight of resin solids.

30 19. In an electrodepositable composition comprising (a) an active hydrogen-containing cationic resin electrodepositable on a cathode; (b) a capped polyisocyanate

AMENDED SHEET (ARTICLE 19)

curing agent; and (c) an organotin-containing catalyst; the improvement comprising the presence in the electrodepositable composition of at least one water immiscible acid functional compound having a hydrocarbon chain of at least 5 carbon atoms
5 selected from the group consisting of abietic acid and natural sources thereof.

20. The electrodepositable composition of claim 19 in which the cationic resin is derived from a polyepoxide.
10

21. The electrodepositable composition of claim 20 in which the polyepoxide is a polyglycidyl ether of a polyhydric alcohol.

22. The electrodepositable composition of claim 20 in which the cationic resin contains salt groups which are amine salt groups.
15

23. The electrodepositable composition of claim 22 in which the amine salt groups are derived from basic nitrogen groups neutralized with an acid selected from the group consisting of formic acid, acetic acid, lactic acid, phosphoric acid, sulfamic acid, and mixtures thereof.
20

24. The electrodepositable composition of claim 19 in which the acid functional compound is a monocarboxylic acid.
25

25. The electrodepositable composition of claim 19 in which the acid functional compound is polycyclic.
30

26. The electrodepositable composition of claim 1 in which the organotin-containing catalyst is present in amounts of

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 97/13367

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C09D5/44 C08G18/16

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09D C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	WO 96 12771 A (PPG INDUSTRIES INC.) 2 May 1996 see claims -----	8, 19-28 1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

13 November 1997

Date of mailing of the international search report

09/12/1997

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Girard, Y

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/US 97/13367

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9612771 A	02-05-96	AU 3593995 A EP 0788528 A	15-05-96 13-08-97